

### Electric steel

Steel grade	Nominal thickness	P15/50 (W/kg) ≤ Core loss	B50 (T) ≥ Magnetic induction intensity	≥ Lamination factor
SG50W470	0.50	4.50	1.64	97
SG50W540		5.20	1.65	
SG50W600		5.40	1.66	
SG50W700		6.50	1.70	
SG50W800		7.50	1.70	
SG50W1000		9.00	1.74	
SG50W1300		11.50	1.73	
SG65W600	0.65	5.80	1.66	97
SG65W700		6.80	1.67	
SG65W800		7.50	1.70	
SG65W1000		8.50	1.71	
SG65W1300		11.50	1.71	
SG65W1600		15.00	1.71	
SG50RW500	0.50	5.00	1.72	96
SG50RW600		6.00	1.72	
SG50HW470	0.50	4.70	1.67	96
SG50HW600		6.00	1.69	
SG50HW800		8.00	1.73	
SG50HW1000		10.00	1.75	

Thickness Scope: 900~1250mm。

Strip Coil Inner diameter: 508mm。

Strip Coil External diameter: 950~1550mm。

Coating type: Semi-organic light coating(S1), Semi-organic heavy coating(S2), Chromium-free environmental protection coating(S3), Inorganic coating(S4)